

CPI®-1507 Series

Specialty Gas Compressor Lubricants



Description

The **CPI®-1507 Series** compressor lubricants are formulated using a premium polyalkylene glycol (PAG) base fluid combined with a high performance additive package. They are specifically formulated to give negligible dilution with hydrocarbon gases.

These compressor lubricants feature excellent oxidative and thermal stability enabling the use of these lubricants over a wide range of temperatures without varnish or deposit formation. The high viscosity index (VI) and negligible hydrocarbon dilution enables the **CPI®-1507 Series** lubricants to operate over wide ranges of temperature and gas composition with small changes in viscosity compared to other types of lubricants.

The **CPI®-1507 Series** fluids are especially advantageous in high temperature and heavy gas stream applications due to their excellent thermal and oxidative stability and negligible hydrocarbon dilution.

Applications and Compressor Type

- Flooded rotary screw compressors
- Heavy hydrocarbon gas stream applications
- Centrifugal compressors
- Liquid ring vacuum pumps

Features and Benefits

Hydrocarbon insoluble	Negligible dilution due to hydrocarbons in operation
Excellent lubricity	Increased efficiency and reduced cost of operation
Oxidatively stable	Longer system life
High viscosity index	Small viscosity changes over wide temperature ranges

Typical Properties*

Test Procedure	ASTM Test Method	CPI®-1507-32	CPI®-1507-46	CPI®-1507-68	CPI®-1507-100	CPI®-1507-150
Kinematic Viscosity, cSt	D445					
40°C		30.96	46.0	63.12	85.26	113.6
100°C		5.32	7.19	9.1	11.37	17.43
Viscosity Index	D2270	104	116	121	123	169
Density, g/mL	D4052					
15.6°C		-	-	1.1466	1.1515	1.1405
20.0°C		1.1305	1.1376	1.1431	1.1480	1.1369
Flash and Fire Point, °C	D92					
Flash Point		206	224	236	239	267
Fire Point		208	224	248	241	281
Pour Point, °C	D5950	-54	-48	-46	-44	-17
Foaming Tendency mL	D892					
Sequence I		0/0	20/0	120/0	140/0	50/0
Sequence II		0/0	10/0	20/0	30/0	40/0
Sequence III		20/0	20/0	210/0	210/0	60/0
Copper Strip Corrosion	D130	1B	1B	1A	1B	1A
Rust Test	D665					
Part A – Distilled Water		Pass	Pass	Pass	Pass	Pass

*These values are not intended for use in preparing specifications

CPI Fluid Engineering
www.cpifluideng.com

North and South America
The Lubrizol Corporation
2300 James Savage Road
Midland, MI 48642, USA

Telephone: 1 (989) 496-3780
Email: sales@cpifluideng.com

Europe, Middle East and Africa
Lubrizol Limited
Pavilion One, Belasis Court
Greenwood Road
Stockton-on-Tees
TS23 4AZ, UK

Telephone: +44 1642 565266
Email: euafricamesales@cpifluideng.com

Asia-Pacific
Lubrizol Southeast Asia (Pte) Ltd
44 Tanjung Penjuru
Singapore 609032

Telephone: + 65-66638 684
Email: asiasales@cpifluideng.com

